

Columbia Coatings

# Technical Data Sheet

Columbia Coatings  
1173 Industrial Park Rd  
Columbia, TN 38401  
931-388-7730  
931-388-5573 FAX



**COLUMBIA**  
COATINGS

<b>Number:</b>	W6779001
<b>Name:</b>	Out Gas Builder Primer
<b>Type:</b>	TGIC

## Powder Properties

<b>Specific Gravity</b>	1.48
<b>Storage Temp</b>	80°F (27°C) up to 1 yr
<b>Theoretical Coverage</b>	43.6 SQ.FT ./LB. @ 2 MILS
<b>Particle Distribution</b>	25 - 50 MICRONS AVERAGE

## Coating Properties

<b>Film Thickness</b>	Recommended film thickness 2.0 to 4.0 mils
<b>Cure Schedule</b>	15 - 18 MINUTES @ 385 DEGREES F.
<b>Gloss Level</b>	n/a
<b>Pencil Hardness</b>	2H
<b>Flexibility</b>	100%
<b>Adhesion</b>	4B
<b>Direct Impact</b>	n/a
<b>Reverse Impact</b>	n/a
<b>Salt Spray</b>	1000 hrs less than 1/16" in creepage over B-1000 treated test panels (ASTM B117)