

Columbia Coatings

Technical Data Sheet

Columbia Coatings
1173 Industrial Park Rd
Columbia, TN 38401
931-388-7730
931-388-5573 FAX



Number:	RAL5020
Name:	RAL 5020
Type:	TGIC

Powder Properties

Specific Gravity	Approx. 1.5
Storage Temp	80°F (27°C)
Theoretical Coverage	128 sq. ft./lb/1 mil
Particle Distribution	n/a

Coating Properties

Film Thickness	Recommended film thickness 2.5 to 3.5 mils
Cure Schedule	7 minutes at 400°F (204°C) or 10 minutes at 375°F (191°C) or 15 minutes at 350°F (177°C) (metal temperature)
Gloss Level	85 ± 3 units on 60°
Pencil Hardness	H - 2H (ASTM D3363)
Flexibility	3/16" (ASTM D522)(Conical Mandrel)
Adhesion	5B
Direct Impact	160 in-lb direct;
Reverse Impact	160 in-lb reverse (ASTM D2794)
Salt Spray	1000 hrs less than 1/16" in creepage over B-1000 treated test panels (ASTM B117)

www.columbiacoatings.com