

Columbia Coatings

Technical Data Sheet

Columbia Coatings
1173 Industrial Park Rd
Columbia, TN 38401
931-388-7730
931-388-5573 FAX



Number:	T1696013
Name:	Shimmer Candy Mahogany TGIC
Type:	TGIC

Powder Properties

Specific Gravity	1.2 – 1.8 g/cm ³
Storage Temp	6 months @ 77°F (25°C)
Theoretical Coverage	51.5 ft ² /lb (11.1 m ² /kg)
Particle Distribution	n/a

Coating Properties

Film Thickness	3.5 – 4.5 mils
Cure Schedule	Metal Temperature: 8 min @ 400°F 15 min @ 375°F
Gloss Level	80 – 90% @ 60°
Pencil Hardness	2H minimum
Flexibility	1/8" Mandrel
Adhesion	5B
Direct Impact	80 in/lb
Reverse Impact	N/A
Salt Spray	1/32 in (1mm) @ 500 hours

www.columbiacoatings.com