

Columbia Coatings

# Technical Data Sheet

Columbia Coatings  
1173 Industrial Park Rd  
Columbia, TN 38401  
931-388-7730  
931-388-5573 FAX



<b>Number:</b>	E2903007
<b>Name:</b>	Weathered Green Urethane
<b>Type:</b>	TGIC

## Powder Properties

<b>Specific Gravity</b>	1.67 +/- .05
<b>Storage Temp</b>	80°F (27°C) up to 1 yr
<b>Theoretical Coverage</b>	47 sq/ft @ 2.5 mils
<b>Particle Distribution</b>	+44 MICRONS (325 MESH) 70 - 80%

## Coating Properties

<b>Film Thickness</b>	Recommended film thickness 2.5 – 4.0 MILS
<b>Cure Schedule</b>	16 MINUTES @ 375°F 25 MINUTES @ 350°F
<b>Gloss Level</b>	ASTM D523 3 - 6%
<b>Pencil Hardness</b>	ASTM D3363 2H
<b>Flexibility</b>	1/8" ASTM D522
<b>Adhesion</b>	5B
<b>Direct Impact</b>	20 in-lb direct;
<b>Reverse Impact</b>	20 in-lb reverse (ASTM D2794)
<b>Salt Spray</b>	1000 hrs less than 1/16" in creepage over B-1000 treated test panels (ASTM B117)

[www.columbiacoatings.com](http://www.columbiacoatings.com)