

Columbia Coatings

# Technical Data Sheet

Columbia Coatings  
1173 Industrial Park Rd  
Columbia, TN 38401  
931-388-7730  
931-388-5573 FAX



<b>Number:</b>	X4339004
<b>Name:</b>	White Vein TGIC
<b>Type:</b>	Polyester

## Powder Properties

<b>Specific Gravity</b>	1.68
<b>Storage Temp</b>	80°F (27°C) up to 1 yr
<b>Theoretical Coverage</b>	57.5 SQ.FT ./LB. @ 2 MILS
<b>Particle Distribution</b>	25 - 50 MICRONS AVERAGE

## Coating Properties

<b>Film Thickness</b>	Recommended film thickness 2.5 to 4.0 mils
<b>Cure Schedule</b>	10 MINUTES @ 400 DEGREES F.
<b>Gloss Level</b>	50% +/-5%
<b>Pencil Hardness</b>	2H
<b>Flexibility</b>	100%
<b>Adhesion</b>	4B
<b>Direct Impact</b>	60 in-lb direct;
<b>Reverse Impact</b>	60 in-lb reverse (ASTM D2794)
<b>Salt Spray</b>	1000 hrs less than 1/16" in creepage over B-1000 treated test panels (ASTM B117)

[www.columbiacoatings.com](http://www.columbiacoatings.com)