



Highlights

PPG's Enviracryl™ and Envirocron™ powder coatings are aesthetically pleasing, produce a durable uniform finish and can be custom formulated with finishes from high gloss to low gloss, and in a variety of textures.

PPG's "World Class" Polyester Urethane Powder Coatings provide a combination of good physical and chemical resistance properties. This extensive line of Polyester Urethane Powders is manufactured to meet the increasing requirement demands of the automotive and industrial markets. These sophisticated Polyester Urethanes are the solution to your smoothness, low-bake, durability and physical property requirements. An unsurpassed application development program enables consistently friendly use on a variety of substrates.

Product Features

- Available in a wide range of colors and glosses
- Exterior durability
- Good chemical resistance
- Thin film capabilities

Technical Properties

Property	Test Method	Value
Color		Blue Transparent PU9006
Appearance		Smooth
Gloss	ASTM D-523	90 Minimum @ 60°
Adhesion	ASTM D-3359	100% (5B Pass)
Hardness	ASTM D-3363	2H Pencil (Eagle)
Impact Resistance	ASTM D-2794	160 In.-lbs. Direct 160 In.-lbs. Reverse
Conical Mandrel	ASTM D-522	1/8" - No Cracking
Salt Spray	ASTM B-117	1000 Hrs. Pass
Humidity	ASTM D-1735	100F, 100% RH - 1000+ hours

Film Properties were determined using 2.0 - 3.0 mils powder film over 22 gauge (0.032") cold rolled steel B1000 test panels.

Application Data

Application Type:	Electrostatic Spray
Recommended Bake:	10 Minutes at 400 °F Metal Temperature See Cure Curve PCU-028
Specific Gravity:	1.19 ± .05
Theoretical Coverage:	161 Sq. Ft. per pound at 1.0 mil
Shelf Life from Date of Manufacture (@40-60% RH):	77 °F Maximum - 12 Months

PPG recommends that all material be used in FIFO order (first in - first out). Materials that exceed the recommended shelf life should be tested prior to use.



* Statements and methods described herein are based upon the best information and practices known to PPG Industries, Inc. ("PPG"). Any statements or methods mentioned herein are general suggestions only and are not to be construed as representations or warranties as to safety, performance, or results. Since the suitability and performance of the product is highly dependent on the product user's processes, operations, and numerous other user-determined conditions, the user is solely responsible for, and assumes all responsibility, risk and liability arising from, the determination of whether the product is suitable for the user's purposes, including without limitation substrate, application process, pasteurization and/or processing, and end use. No testing, suggestions or data offered by PPG to the user shall relieve the user of this responsibility. PPG does not warrant freedom from patent infringement in the use of any formula or process set forth herein. Continuous improvements in coatings technology may cause future technical data to vary from what is in this bulletin. Contact your PPG representative for the most up to date information.

ENVIROCRON and the PPG logo is a registered trademarks of PPG Industries Ohio, Inc.