

Columbia Coatings

Technical Data Sheet

Columbia Coatings
1173 Industrial Park Rd
Columbia, TN 38401
931-388-7730
931-388-5573 FAX



| | |
|----------------|-----------|
| Number: | I1798019 |
| Name: | AG Yellow |
| Type: | TGIC |

Powder Properties

| | |
|------------------------------|----------------------------------|
| Specific Gravity | 1.47 +/- 0.05 |
| Storage Temp | < 77°F (25°C) |
| Theoretical Coverage | 131 ft ² /lb. @ 1 mil |
| Particle Distribution | n/a |

Coating Properties

| | |
|------------------------|--|
| Film Thickness | 3.5-4.5 mils |
| Cure Schedule | Metal Temperature: 10 minutes @ 400°F (204°C) |
| Gloss Level | 90% |
| Pencil Hardness | H-2H |
| Flexibility | n/a |
| Adhesion | n/a |
| Direct Impact | 160 in/lb. |
| Reverse Impact | 160 in/lb. |
| Salt Spray | 1000 hrs. |

www.columbiacoatings.com