

Columbia Coatings

Technical Data Sheet

Columbia Coatings
1173 Industrial Park Rd
Columbia, TN 38401
931-388-7730
931-388-5573 FAX



COLUMBIA
COATINGS

Number:	S5700092
Name:	Bomber Black
Type:	Polyester

Powder Properties

Specific Gravity	Approx. 1.64 g/cm ³
Storage Temp	< 77°F (25°C)
Theoretical Coverage	177 sq. ft/lb. @ 1 mil
Particle Distribution	n/a

Coating Properties

Film Thickness	Recommended Film Thickness: 2–3 mils
Cure Schedule	Metal Temperature: 10 minutes at 400°F (204°C)
Gloss Level	0-3% @ 60°
Pencil Hardness	2H (ASTM D3363)
Flexibility	1/8" (ASTM D522) (Conical Mandrel)
Adhesion	5B (ASTM D3359)
Direct Impact	60 in-lb. direct (ASTM D2794)
Reverse Impact	60 in-lb. direct (ASTM D2794)
Salt Spray	3000 Hrs. Pass

www.columbiacoatings.com