# PPG Military Powder Coat

## MILITARY DEFENSE Military Powder Coat MLP50001

### PPG Powder Coatings

#### **Highlights**

PPG's Envirocron™ powder coatings are aesthetically pleasing, produce a durable uniform finish and can be custom formulated with finishes from high gloss to low gloss, and in a variety of textures.

PPG's "World Class" Polyester Powder Coatings provide a combination of good physical and chemical resistance properties. This extensive line of Polyester Powders is manufactured to meet the increasing requirement demands of many industrial markets. These sophisticated Polyesters are the solution to your smoothness, low-bake, durability and physical property requirements. An unsurpassed application development program enables consistently friendly use on a variety of substrates.

#### **Product Features**

This is a NON CARC product Exterior durability Good chemical resistance UL Approved

### **Technical Properties**

Property	Test Method	Value
Color Appearance		Air Force Blue N5804EA Smooth
Gloss	ASTM D-523	85 Minimum @ 60°
Adhesion	ASTM D-3359	100% (5B Pass)
Hardness	ASTM D-3363	H - 2H Pencil (Eagle)
Impact Resistance	ASTM D-2794	80 InIbs. Direct
		80 InIbs. Reverse
Conical Mandrel	ASTM D-522	1/8" Mandrel - No Cracking
Salt Spray	ASTM B-117	1000 Hrs. Pass <1/8" Scribe Creep - No Blisters
Humidity	ASTM D-2247	1000 Hrs. Pass <1/16" Scribe Creep - No Blisters

Film Properties were determined using 2.0 - 3.0 mils powder film over iron phosphated, chrome rinse pretreated, 22 gauge, unpolished cold rolled steel test panels.

#### **Application Data**

Application Type:	Electrostatic Spray
Recommended Bake:	10 Minutes at 400 °F Metal Temperature
	See Cure Curve MLP-001
Specific Gravity:	1.61 ± .05
Theoretical Coverage:	119 Sq. Ft. per pound at 1.0 mil
Shelf Life from Date of Manufacture (@ 40-60% RH):	80 °F Maximum - 24 Months

PPG recommends that all material be used in FIFO order (first in - first out). Materials that exceed the recommended shelf life should be tested prior to use.

\* Statements and methods described herein are based upon the best information and practices known to PPG Industries, Inc. ("PPG"). Any statements or methods mentioned herein are general suggestions only and are not to be construed as representations or warranties as to safety, performance, or results. Since the suitability and performance of the product is highly dependent on the product user's processes, operations, and numerous other user-determined conditions, the user is solely responsible for, and assumes all responsibility, risk and liability arising from, the determination of whether the product is usuable for the user's purposes, including without limitation substrate, application process, pasteurization and /or processing, and end use. No testing, suggestions or data offered by PPG to the user shall releve the user of this responsibility. PPG does not warrant freedom from patent in thringement in the use of any formula or process efforth herein. Continuous improvements in coatings technology may cause future technical data to vary from what is in this bulletin. Contact your PPG representative for the most up to date information.

PPG logo are registered trademarks of PPG Industries Ohio, Inc.

PPG Industries, Inc. 19699 Progress Drive Strongsville, OH 44149 800-450-2652 http://governmentsolutions.ppg.com

PPG GOVERNMENT SOLUTIONS MILITARY DEFENSE I HOMELAND SECURITY I CONSTRUCTION I FLEET VEHICLES

7/15/2021