

Columbia Coatings

Technical Data Sheet

Columbia Coatings
1173 Industrial Park Rd
Columbia, TN 38401
931-388-7730
931-388-5573 FAX



Number:	T1693003
Name:	Shimmer Candy Lime Green
Type:	TGIC

Powder Properties

Specific Gravity	1.2-1.8 g/cm ³
Storage Temp	6 months @ 77°F (25°C)
Theoretical Coverage	51.5 ft ² /lb.
Particle Distribution	n/a

Coating Properties

Film Thickness	3.5-4.5 mils
Cure Schedule	Metal Temperature: 8 minutes @ 400°F (204°C) 15 minutes @ 375°F (191°C)
Gloss Level	80-90%
Pencil Hardness	2H minimum
Flexibility	1/8" mandrel
Adhesion	5B
Direct Impact	80 in/lb.
Reverse Impact	n/a
Salt Spray	1/32" @ 500 hours

www.columbiacoatings.com