

Columbia Coatings

# Technical Data Sheet

Columbia Coatings  
1173 Industrial Park Rd  
Columbia, TN 38401  
931-388-7730  
931-388-5573 FAX



<b>Number:</b>	E2220001
<b>Name:</b>	Silver Bronze Hammertone Urethane
<b>Type:</b>	TGIC

## Powder Properties

<b>Specific Gravity</b>	1.60 +/- .05
<b>Storage Temp</b>	80°F (27°C) up to 1 year
<b>Theoretical Coverage</b>	40 sq./ft @ 2.5 mils
<b>Particle Distribution</b>	+44 MICRONS (325 MESH) 30 - 35%

## Coating Properties

<b>Film Thickness</b>	Recommended film thickness 2.5 - 3.5 MILS
<b>Cure Schedule</b>	Metal Temperature: 16 minutes @ 375°F (191°C) 25 minutes @ 350°F (177°C)
<b>Gloss Level</b>	ASTM D523 25 - 45%
<b>Pencil Hardness</b>	ASTM D3363 H-2H
<b>Flexibility</b>	1/8" ASTM D522
<b>Adhesion</b>	5B
<b>Direct Impact</b>	120 in-lb. direct;
<b>Reverse Impact</b>	120 in-lb. reverse (ASTM D2794)
<b>Salt Spray</b>	1000 hrs. less than 1/16" in creepage over B-1000 treated test panels (ASTM B117)

[www.columbiacoatings.com](http://www.columbiacoatings.com)