

Columbia Coatings

Technical Data Sheet

Columbia Coatings
1173 Industrial Park Rd
Columbia, TN 38401
931-388-7730
931-388-5573 FAX



Number:	X1262043
Name:	Silver Hammertone II
Type:	TGIC

Powder Properties

Specific Gravity	1.22
Storage Temp	80°F (27°C) up to 1 year
Theoretical Coverage	157.0 SQ. FT./LB. @ 1 MILS
Particle Distribution	25 - 50 MICRONS AVERAGE

Coating Properties

Film Thickness	Recommended film thickness: 3 - 5 mils
Cure Schedule	Metal Temperature: 10 minutes @ 400°F (204°C)
Gloss Level	35-45%
Pencil Hardness	H-2H
Flexibility	100%
Adhesion	4B
Direct Impact	80 in-lb. direct;
Reverse Impact	80 in-lb. reverse (ASTM D2794)
Salt Spray	500 hrs. less than 1/16" in creepage over B-1000 treated test panels (ASTM B117)

www.columbiacoatings.com