

Columbia Coatings

Technical Data Sheet

Columbia Coatings
1173 Industrial Park Rd
Columbia, TN 38401
931-388-7730
931-388-5573 FAX



| | |
|----------------|---------------------------|
| Number: | NHL178629 |
| Name: | Columbus Blue Jackets Red |
| Type: | TGIC |

Powder Properties

| | |
|------------------------------|--------------------------------|
| Specific Gravity | Approx. 1.50 g/cm ³ |
| Storage Temp | < 80°F (27°C) |
| Theoretical Coverage | 128 sq. ft/lb. @ 1 mil |
| Particle Distribution | n/a |

Coating Properties

| | |
|------------------------|----------------------------------------------------------------|
| Film Thickness | Recommended Film Thickness: 2.5–3.5 mils |
| Cure Schedule | Metal Temperature: 10 minutes at 400°F (204°C) |
| Gloss Level | 80% @ 60° |
| Pencil Hardness | 2H (ASTM D3363) |
| Flexibility | 1/8" (ASTM D522) (Conical Mandrel) |
| Adhesion | 5B (ASTM D3359) |
| Direct Impact | 100 in-lb. direct (ASTM D2794) |
| Reverse Impact | 100 in-lb. direct (ASTM D2794) |
| Salt Spray | 1000 Hrs. Pass <1/8" Scribe Creep - No Blisters (ASTM B117) |

www.columbiacoatings.com