

Columbia Coatings

# Technical Data Sheet

Columbia Coatings  
1173 Industrial Park Rd  
Columbia, TN 38401  
931-388-7730  
931-388-5573 FAX



<b>Number:</b>	U1698043
<b>Name:</b>	Illusion Mossy Gold
<b>Type:</b>	TGIC

## Powder Properties

<b>Specific Gravity</b>	1.36 ( $\pm$ 0.05) g/cm <sup>3</sup>
<b>Storage Temp</b>	6 months @ 77°F (25°C)
<b>Theoretical Coverage</b>	141.39 ft <sup>2</sup> /lb. @ 1 mil
<b>Particle Distribution</b>	n/a

## Coating Properties

<b>Film Thickness</b>	Recommended Film Thickness: 2 – 3 mils
<b>Cure Schedule</b>	Partial Cure: 15 min. total time in oven preheated to 400°F. Then apply our Super Mirror Clear and fully cure. * This powder requires a clear coat for the Illusion Effect
<b>Gloss Level</b>	80 – 90% @ 60°
<b>Pencil Hardness</b>	H (ASTM D3363)
<b>Flexibility</b>	1/8" (ASTM D522) (Conical Mandrel)
<b>Adhesion</b>	100% (ASTM D3359)
<b>Direct Impact</b>	40/40 or better (ASTM D2794)
<b>Reverse Impact</b>	40/40 or better (ASTM D2794)
<b>Salt Spray</b>	1/16" creep @ 500 hrs. (ASTM B117)

[www.columbiacoatings.com](http://www.columbiacoatings.com)