

Columbia Coatings

Technical Data Sheet

Columbia Coatings
12683 McIlwain Rd,
Holladay, TN 38341
931-388-7730
931-388-5573 FAX



COLUMBIA
COATINGS

Number:	X1902021
Name:	Dark Silver Texture TGIC
Type:	TGIC

Specific Gravity	1.55 +/- .05
Storage Temp	80°F (27°C) up to 1 year
Theoretical Coverage	62 sq./ft @ 2.0 mils
Particle Distribution	+44 MICRONS (325 MESH) 35 - 45%

Powder Properties

Film Thickness	Recommended film thickness 2.0 – 3.0 MILS
Cure Schedule	Metal Temperature: 18 minutes @ 375°F (191°C) 25 minutes @ 350°F (177°C)
Gloss Level	ASTM D523 3 - 5%
Pencil Hardness	ASTM D3363 2H
Flexibility	1/8" ASTM D522
Adhesion	5B
Direct Impact	160 in-lb. direct;
Reverse Impact	140 in-lb. reverse (ASTM D2794)
Salt Spray	1000 hrs. less than 1/16" in creepage over B-1000 treated test panels (ASTM B117)

Coating Properties