

Columbia Coatings

Technical Data Sheet

Columbia Coatings
12683 McIlwain Rd
Holladay, TN 38341
931-388-7730
931-388-5573 FAX



Number:	M8798093
Name:	Haunted Halo
Type:	Acrylic

Specific Gravity	1.16 ($\pm$ 0.05) g/cm ³
Storage Temp	70°F (21°C)
Theoretical Coverage	165 ft ² /lb. @ 1 mil
Particle Distribution	n/a

Powder Properties

Film Thickness	Recommended Film Thickness: 2 – 4 mils
Cure Schedule	Metal Temperature: 17 minutes @ 350°F (177°C)
Gloss Level	80+% @ 60°
Pencil Hardness	H (ASTM D3363)
Flexibility	n/a
Adhesion	100% (ASTM D3359)
Direct Impact	20 in/lb. (ASTM D2794)
Reverse Impact	20 in/lb. (ASTM D2794)
Salt Spray	1000 hrs. less than 1/16" in creepage over B-1000 treated test panels (ASTM B117)

Coating Properties