

Columbia Coatings

# Technical Data Sheet

Columbia Coatings  
12683 McIlwain Rd  
Holladay, TN 38341  
931-388-7730  
931-388-5573 FAX



|                |                      |
|----------------|----------------------|
| <b>Number:</b> | RAL7011              |
| <b>Name:</b>   | RAL 7011 – Iron Grey |
| <b>Type:</b>   | TGIC                 |

|                              |                                |
|------------------------------|--------------------------------|
| <b>Specific Gravity</b>      | Approx. 1.50 g/cm <sup>3</sup> |
| <b>Storage Temp</b>          | < 80°F (27°C)                  |
| <b>Theoretical Coverage</b>  | 128 sq. ft/lb. @ 1 mil         |
| <b>Particle Distribution</b> | n/a                            |

## Powder Properties

|                        |                                                                |
|------------------------|----------------------------------------------------------------|
| <b>Film Thickness</b>  | Recommended Film Thickness: 2.5–3.5 mils                       |
| <b>Cure Schedule</b>   | Metal Temperature:<br>10 minutes at 400°F (204°C)              |
| <b>Gloss Level</b>     | 80% @ 60°                                                      |
| <b>Pencil Hardness</b> | 2H (ASTM D3363)                                                |
| <b>Flexibility</b>     | 1/8" (ASTM D522) (Conical Mandrel)                             |
| <b>Adhesion</b>        | 5B (ASTM D3359)                                                |
| <b>Direct Impact</b>   | 100 in-lb. direct (ASTM D2794)                                 |
| <b>Reverse Impact</b>  | 100 in-lb. direct (ASTM D2794)                                 |
| <b>Salt Spray</b>      | 1000 Hrs. Pass <1/8" Scribe Creep<br>- No Blisters (ASTM B117) |

## Coating Properties