

Columbia Coatings

# Technical Data Sheet

Columbia Coatings  
12683 McIlwain Rd  
Holladay, TN 38341  
931-388-7730  
931-388-5573 FAX



**COLUMBIA**  
COATINGS

<b>Number:</b>	CS8694067
<b>Name:</b>	Sonic Blast
<b>Type:</b>	Acrylic

<b>Specific Gravity</b>	1.16 ( $\pm$ 0.05) g/cm <sup>3</sup>
<b>Storage Temp</b>	< 70°F (21°C)
<b>Theoretical Coverage</b>	166 ft <sup>2</sup> /lb. @ 1 mil
<b>Particle Distribution</b>	n/a

## Powder Properties

<b>Film Thickness</b>	Recommended Film Thickness: 2 - 4 mils
<b>Cure Schedule</b>	Metal Temperature: 17 minutes @ 350°F (177°C)
<b>Gloss Level</b>	90+% @ 60°
<b>Pencil Hardness</b>	H – 2H (ASTM D3363)
<b>Flexibility</b>	1/8" (ASTM D522) (Conical Mandrel)
<b>Adhesion</b>	100% (ASTM D3359)
<b>Direct Impact</b>	20 in/lb. (ASTM D2794)
<b>Reverse Impact</b>	20 in/lb. (ASTM D2794)
<b>Salt Spray</b>	1000 hrs. less than 1/16" in creepage over B-1000 treated test panels (ASTM B117)

## Coating Properties