

Columbia Coatings

Technical Data Sheet

Columbia Coatings
12683 McIlwain Rd,
Holladay, TN 38341
931-388-7730
931-388-5573 FAX



| | |
|----------------|----------------|
| Number: | S1794109 |
| Name: | Deep Turquoise |
| Type: | TGIC |

Powder Properties

| | |
|------------------------------|--------------------------------|
| Specific Gravity | Approx. 1.20 g/cm ³ |
| Storage Temp | < 77°F (25°C) |
| Theoretical Coverage | 161 sq. ft/lb. @ 1 mil |
| Particle Distribution | n/a |

Coating Properties

| | |
|------------------------|--|
| Film Thickness | Recommended Film Thickness: 2–3 mils |
| Cure Schedule | Metal Temperature: 10 minutes at 400°F (204°C) |
| Gloss Level | 90+% @ 60° |
| Pencil Hardness | H-2H (ASTM D3363) |
| Flexibility | 1/8" (ASTM D522) (Conical Mandrel) |
| Adhesion | 5B (ASTM D3359) |
| Direct Impact | 100 in-lb. direct (ASTM D2794) |
| Reverse Impact | 100 in-lb. direct (ASTM D2794) |
| Salt Spray | 2000 Hrs. Pass <1/8" Scribe Creep - No Blisters (ASTM B117) |

www.columbiacoatings.com