

Columbia Coatings

Technical Data Sheet

Columbia Coatings
12683 McIlwain Rd
Holladay, TN 38341
931-388-7730
931-388-5573 FAX



| | |
|----------------|-------------|
| Number: | S1706112 |
| Name: | Light Lilac |
| Type: | TGIC |

| | |
|------------------------------|------------------------------|
| Specific Gravity | 1.68 ± .05 g/cm ³ |
| Storage Temp | Maximum 80°F (27°C) |
| Theoretical Coverage | 115 sq./ft @ 1 mil |
| Particle Distribution | n/a |

Powder Properties

| | |
|------------------------|--|
| Film Thickness | Recommended film thickness: 2 – 3 mils |
| Cure Schedule | Metal Temperature: 10 minutes @ 400°F (204°C) |
| Gloss Level | 0 – 10% @ 60° |
| Pencil Hardness | H-2H |
| Flexibility | 3/8" |
| Adhesion | 5B |
| Direct Impact | 160 in/lb. |
| Reverse Impact | 160 in/lb. |
| Salt Spray | 1000 hrs. |

Coating Properties