

Columbia Coatings

Technical Data Sheet

Columbia Coatings
12683 McIlwain Rd,
Holladay, TN 38341
931-388-7730
931-388-5573 FAX



Number:	M1642104
Name:	Diesel Dust
Type:	TGIC

Powder Properties

Specific Gravity	Approx. 1.61 g/cm ³
Storage Temp	< 80°F (27°C)
Theoretical Coverage	119 sq. ft/lb. @ 1 mil
Particle Distribution	n/a

Coating Properties

Film Thickness	Recommended Film Thickness: 2.0–3.0 mils
Cure Schedule	Metal Temperature: 10 minutes at 340°F (171°C)
Gloss Level	45-55% @ 60°
Pencil Hardness	2H (ASTM D3363)
Flexibility	1/8" (ASTM D522) (Conical Mandrel)
Adhesion	5B (ASTM D3359)
Direct Impact	160 in-lb. direct (ASTM D2794)
Reverse Impact	160 in-lb. direct (ASTM D2794)
Salt Spray	1000 Hrs. Pass <1/8" Scribe Creep - No Blisters (ASTM B117)

www.columbiacoatings.com